



# Relative Lifetimes of MAPLUB® Greases for Space Applications

Mario Marchetti and William R. Jones, Jr.  
Glenn Research Center, Cleveland, Ohio

Jacques Sicre  
Centre National D'Etudes Spatiales, Toulouse, France

## The NASA STI Program Office . . . in Profile

Since its founding, NASA has been dedicated to the advancement of aeronautics and space science. The NASA Scientific and Technical Information (STI) Program Office plays a key part in helping NASA maintain this important role.

The NASA STI Program Office is operated by Langley Research Center, the Lead Center for NASA's scientific and technical information. The NASA STI Program Office provides access to the NASA STI Database, the largest collection of aeronautical and space science STI in the world. The Program Office is also NASA's institutional mechanism for disseminating the results of its research and development activities. These results are published by NASA in the NASA STI Report Series, which includes the following report types:

- **TECHNICAL PUBLICATION.** Reports of completed research or a major significant phase of research that present the results of NASA programs and include extensive data or theoretical analysis. Includes compilations of significant scientific and technical data and information deemed to be of continuing reference value. NASA's counterpart of peer-reviewed formal professional papers but has less stringent limitations on manuscript length and extent of graphic presentations.
- **TECHNICAL MEMORANDUM.** Scientific and technical findings that are preliminary or of specialized interest, e.g., quick release reports, working papers, and bibliographies that contain minimal annotation. Does not contain extensive analysis.
- **CONTRACTOR REPORT.** Scientific and technical findings by NASA-sponsored contractors and grantees.

- **CONFERENCE PUBLICATION.** Collected papers from scientific and technical conferences, symposia, seminars, or other meetings sponsored or cosponsored by NASA.
- **SPECIAL PUBLICATION.** Scientific, technical, or historical information from NASA programs, projects, and missions, often concerned with subjects having substantial public interest.
- **TECHNICAL TRANSLATION.** English-language translations of foreign scientific and technical material pertinent to NASA's mission.

Specialized services that complement the STI Program Office's diverse offerings include creating custom thesauri, building customized databases, organizing and publishing research results . . . even providing videos.

For more information about the NASA STI Program Office, see the following:

- Access the NASA STI Program Home Page at <http://www.sti.nasa.gov>
- E-mail your question via the Internet to [help@sti.nasa.gov](mailto:help@sti.nasa.gov)
- Fax your question to the NASA Access Help Desk at 301-621-0134
- Telephone the NASA Access Help Desk at 301-621-0390
- Write to:  
NASA Access Help Desk  
NASA Center for AeroSpace Information  
7121 Standard Drive  
Hanover, MD 21076



# Relative Lifetimes of MAPLUB® Greases for Space Applications

Mario Marchetti and William R. Jones, Jr.  
Glenn Research Center, Cleveland, Ohio

Jacques Sicre  
Centre National D'Etudes Spatiales, Toulouse, France

National Aeronautics and  
Space Administration

Glenn Research Center

## Acknowledgments

This work was performed while the first author held a National Research Council Research Associateship Award in the Tribology and Surface Science Branch, NASA Glenn Research Center.

Trade names or manufacturers' names are used in this report for identification only. This usage does not constitute an official endorsement, either expressed or implied, by the National Aeronautics and Space Administration.

Available from

NASA Center for Aerospace Information  
7121 Standard Drive  
Hanover, MD 21076

National Technical Information Service  
5285 Port Royal Road  
Springfield, VA 22100

Available electronically at <http://gltrs.grc.nasa.gov>



# Relative Lifetimes of MAPLUB® Greases for Space Applications

Mario Marchetti\* and William R. Jones, Jr.  
National Aeronautics and Space Administration  
Glenn Research Center  
Cleveland, Ohio 44135

Jacques Sicre  
Centre National D'Etudes Spatiales  
Toulouse, France

## Abstract

A Spiral Orbit Tribometer was employed to evaluate the tribological behavior and relative lifetimes of several commercially available greases under ultrahigh vacuum. These greases are either based on a multiply alkylated cyclopentane oil, or a perfluoropolyalkylether oil, and a thickener made of polytetrafluoroethylene (PTFE) telomer. The multiply alkylated cyclopentane (MAC) greases yielded long lifetimes, while perfluoropolyalkylether (PFPE) greases yielded short lifetimes.

## I- Introduction

Extended mission lifetimes and improvements to other spacecraft components, such as electronics, batteries, and computers have placed increased burdens on space lubrication systems [1]. Liquid or grease lubrication is commonly used to extend lifetimes and minimize wear, torque, and noise [2]. Thus, the reliability of spacecraft moving mechanical assemblies (MMAs) clearly depends on the lubricant employed to assure that mission objectives will be attained. Accelerated testing has become mandatory and critical.

Full scale life testing [3] or actual component testing [4, 5, 6] is desirable, but both are costly and time consuming. Various accelerated tests are available to evaluate the relative lifetime, torque, wear rate, friction coefficient or degradation rate of the lubricant. These include the eccentric bearing test apparatus [7, 8], the vacuum four-ball tribometer [9, 10], and the spiral orbit rolling contact tribometer [11].

The Spiral Orbit Tribometer (SOT) [11] reproduces the kinematics of an angular contact bearing. The lubricated lifetime, friction coefficient, contact resistance, and degradation products can be determined, monitored, and analyzed. The relative lifetimes of lubricants measured with the SOT have correlated well with actual bearing life tests [4]. The lifetime is, indeed, inversely proportional to the degradation rate of the lubricant. The SOT's ability to study oils and solid lubricants has been extended to greases [12, 13, 14], which represent many of the lubricants used in MMAs.

The objective of the work reported here was to compare the tribological behavior of several commercially available greases, which are used for the lubrication of space mechanisms.

## II- Materials and testing

### 1- The Spiral Orbit Tribometer

The Spiral Orbit Tribometer (SOT) simulates an angular contact bearing (Figure 1). A 12.7 mm (1/2 inch) diameter ball rolls between a fixed plate and a rotary plate, running at

---

\*National Research Council—NASA Resident Research Associate at Glenn Research Center.

210 rpm. The load, providing a mean hertzian stress of 1.5 GPa, was applied through the fixed plate. The combination of high load, moderate speed, and of the small amount of lubricant (approximately 50  $\mu\text{g}$ ) allowed the system to operate in the boundary lubrication regime. The ball was rolling and pivoting in a spiral and maintained in the orbit by a guide plate at a mean orbit radius of approximately 21 mm. The force exerted by the ball on the guide plate, and normal to the guide plate, was used to determine the friction coefficient, since the ball was sliding between the disks when also in contact with the guide plate (scrub area). The resistance of the contacts between the ball and the plates was calculated from the voltage drop across the plates. Evaluation of the greases was conducted at room temperature ( $\approx 23^\circ\text{C}$ ), and under ultrahigh vacuum ( $1.3 \cdot 10^{-6}$  Pa). As the lubricant was tribologically stressed, it was degraded and eventually consumed. Test conclusion was defined when a friction coefficient of 0.28 was attained. Normalized lubricant lifetime (or inversely, its degradation rate) was then defined as the number of orbits to failure divided by the initial amount of lubricant in micrograms.

## 2- Materials preparation

Greases considered in this study are either based on a MAC or a PFPE oil and a tetrafluoroethylene telomer as a thickener. They were developed at INSA Lyon (France), in collaboration with CNES (French Space Agency) [15]. Their characteristics and properties are summarized in Table 1. For comparison, data for Rheolube<sup>®</sup> 2000 and Krytox<sup>®</sup> 240AC, both greases for space applications, are also given.

For the SOT tests, the greases were applied only to the ball by rolling it several times between two elastic membranes made of polyethylene. The small amount of grease deposited on the ball (30 to 60  $\mu\text{g}$ ) was determined using a balance with an accuracy of  $\pm 2$   $\mu\text{g}$ . The edges of the wear tracks on the SOT plates, where some of the lubricant was transferred during the test, were analyzed with an infrared micro-spectrometer. It confirmed that both oil and thickener were present on the ball surface.

All specimens were made of AISI 440C stainless steel. For tribological purposes, ball and plate surfaces were polished to a roughness  $R_a$  of 0.05  $\mu\text{m}$ . The cleaning process, described earlier [16], is based on an alumina slurry, deionized water, drying with filtered nitrogen, and exposure to UV/ozone.

## III- Tribological response of the greases

### 1- Normalized Lifetime

All greases were tested three times with the SOT. The data, reported in Figure 2, clearly show the lifetimes of the MAC-greases to be much greater than PFPE-greases by three orders of magnitude. The results obtained were consistent with the ones from Rheolube<sup>®</sup> 2000 [13] and Krytox<sup>®</sup> 240AC [14], two others greases used for space. The presence of  $\text{MoS}_2$  in the PFPE-grease did not improve its lifetime, as was the case with the MAC-grease.

### 2- Friction Coefficient

The friction traces (Figures 3 and 4) of the MAPLUB<sup>®</sup> greases changed with the base oil used. In the case of PFPE-greases, the friction coefficient was higher (0.12 to 0.13) than with the MAC-greases (0.09 to 0.10). The MAC-greases have shown a long lifetime, and had a greater ability to lubricate the contact than the PFPE had.



The way the friction coefficient increased during the tests changes from one grease to the other. In the case of PFPE-greases, the friction coefficient was nearly steady, and then increased sharply at failure. The MAC-greases have shown a more progressive and continuous increase, and no abrupt failure (Figure 3). Arrows in Figures 3 and 4 indicate changes in the friction traces of the different lubricants, putting in evidence several stages to be discussed below.

#### IV- Discussion

The lifetimes obtained with these greases are consistent with the ones previously obtained with oils and greases based on similar materials. The results have confirmed the stability of MAC oil in the boundary lubrication regime, while the PFPE based lubricants yielded very low lifetimes due to the autocatalytic degradation mechanism. The PFPE-greases can only be safely used with materials reducing degradation, such as TiC [17], ion-implantation of nitrogen [18] or  $\text{Si}_3\text{N}_4$  or TiN [19], some of which are now being used in various space mechanisms.

The presence of  $\text{MoS}_2$  improved the lifetime of the MAC-grease by about 50% but  $\text{MoS}_2$  presence did not affect the PFPE-based grease lifetime. An improvement due to the presence of  $\text{MoS}_2$  in grease was already shown in the past [20], and can be explained by the small amount of additive within the lubricant.  $\text{MoS}_2$  generally ranged around 1% in volume, enough to provide the grease a black color. Since tests were run with approximately 50  $\mu\text{g}$  of grease deposited on the surface of the ball, there are only traces of  $\text{MoS}_2$ . No traces of this material were detected either on balls or tracks after the tests, using XPS and EDAX analysis (Figure 5). In the case of MAC-grease, the degradation process is slow, so the system can rely on the small amount of  $\text{MoS}_2$  present to improve its lifetime. In the case of the PFPE-grease, it would mean that the lifetime could not be attributed to the traces of additives, due to the quick decomposition of both the oil and the thickener. Another possibility is a chemical reaction between the  $\text{MoS}_2$  and the free radicals usually generated as the lubricant degrades. In all cases, both tracks and ball were covered by a layer of fluorinated friction polymer, a result of the degradation of PTFE and/or the lubricant, shown by XPS analysis. The degradation of the lubricant is faster with the PFPE-grease, allowing the  $\text{MoS}_2$  particles to become quickly embedded in the friction polymer where they are inactive. Moreover, the improvement could be so small that it would be much less than the standard deviation. The more gradual decomposition of the MAC-grease allows the  $\text{MoS}_2$  to reach the tribological surfaces and lubricate the contact.

Some differences have also appeared in the friction traces of the various greases. This aspect was already discussed in a previous paper [13]. Some examples of the friction traces are given in Figures 3 and 4. There is a clear distinction between the traces according to the type of base oil involved.

The friction traces of the MAC-greases show a more progressive failure. It took several thousands orbits to reach the friction limit. On the other hand, the behavior of the PFPE-greases could be divided in three different stages: a short and rapid increase in the friction coefficient, a steady increase region, and then the sudden failure.

The common point between the MAPLUB<sup>®</sup> greases is the type of thickener. All are based on PTFE. As a matter of fact, MAPLUB<sup>®</sup> greases based on MAC have not shown the same behavior as the MAC based Rheolube<sup>®</sup> 2000 (thickener made of an ester soap), which have a precursor of failure described in a former study [13]. The Rheolube<sup>®</sup> 2000 has additives, and a different thickener, which could explain the long lifetime obtained compared

to the corresponding MAPLUB<sup>®</sup>. The combination of a fluorinated thickener and a multiply alkylated cyclopentane base oil has led to a behavior which is a combination of the tribological characteristics of the components. The presence of the MAC as a base oil has led to a greater lifetime, similar to the Rheolube<sup>®</sup> 2000, while the PTFE thickener caused the friction coefficient to increase progressively, as observed with the PFPE-greases (Figure 4). This aspect would suggest that both PTFE and PFPE are subject to degradation.

#### V-Summary of the results

The MAPLUB<sup>®</sup> greases based on Pennzane<sup>®</sup> oil have shown a much greater lifetime than PFPE-based greases. Their lifetimes are of the same order of magnitude as Rheolube<sup>®</sup> 2000, also based on a Pennzane<sup>®</sup> oil. The presence of MoS<sub>2</sub> has increased the lifetime of the MAC-grease. The presence of PTFE compound within the grease caused a progressive and continuous increase in the friction coefficient of the lubricant tested with the SOT.

#### VI-Conclusion

The Spiral Orbit Tribometer is clearly able to make a distinction between the capabilities of different fluid lubricants. According to the composition of the grease (nature of the base oil, thickener, additive), a clear distinction can be made between their tribological response and their friction coefficient trace.

#### VII- References

1. Fleischauer P.D., Hilton M.R., "Assessment of the Tribological Requirements of Advanced Spacecraft Mechanisms," The Aerospace Corporation, El Segundo, CA, Report n° TOF-0090 (5064)-1, 1991
2. Jones W.R., Jr., Jansen M.J., "Modern tribology Handbook – volume 2," Section 4, pp. 1159–1186, CRC Press: Boca Raton, London, New York, Washington D.C. ISBN0-8493-8403-6.
3. Brown P.L., Miller J.B., Jones W.R., Jr., Rasmussen K., Wheeler D.R., Rana M., Peri F., "The Clouds and Earth's Radiant Energy System Elevation Bearing Assembly Life Test," Proceedings of the 33<sup>rd</sup> Space Mechanisms Symposium, May 1999, pp. 197–212.
4. Loewenthal S.H., Jones W.R., Jr., Predmore R., "Life of Pennzane and 815Z-Lubricated Instrument Bearings Cleaned with Non-CFC Solvents," NASA TM–209392, 1999.
5. VanDyk S., Dietz B., Street K., Jones W., Jansen M., Dube M., Sharma R., Predmore R., "The Role of Bearing and Scan Mechanism Life Testing in Flight Qualification of The MODIS Instrument," Proceedings of the 35<sup>th</sup> Aerospace Mechanisms Symposium, May 2001, pp. 1–14.
6. Gill S., Rowntree R.A., "Interim Results from ESTL Studies on Static Adhesion and the Performance of Pennzane SHF X-2000 in Ball Bearings," Proceedings of the 6<sup>th</sup> European Space Mechanisms and Tribology Symposium, Technopark, Zürich, Switzerland, 4–6 October 1995, pp. 279–291.
7. Kalogeras C., Hilton M., Carré D., Didziulis S., Fleischauer P., "The Use of Screening Tests in Spacecraft Lubricant Evaluation," The Aerospace Corporation, El Segundo, CA. Report n° TR-93(3935)-6, 1993.



8. Carré D., Kalogeras C.G., Didziulis S.V., Fleischauer P.D., Bauer R., "Recent Experience with Synthetic Hydrocarbon Lubricants for Spacecraft Applications," The Aerospace Corporation, El Segundo, CA. Report n° TR-95(5935)-3, 1995.
9. Masuko M., Jones W. R., Jr., Jansen R., Ebihara B., Pepper S.V., Helmick L.R., "A Vacuum Four-Ball Tribometer to Evaluate Liquid Lubricants for Space Applications," *Lubrication Engineering*, volume 50 (1995) 871.
10. Jones W.R., Jr., Poslowski A.K., Shogrin B.A., Herrera-Fierro P., Jansen M.J., "Evaluation of Several Space Lubricants Using a Vacuum Four-Ball Tribometer." NASA TM-208654, 1998.
11. Jones W.R., Jr., Pepper S.V., Jansen M.J., Nguyen Q.N., Kingsbury E.P., Loewenthal S., Predmore R., "A New Apparatus to Evaluate Lubricants for Space Applications – The Spiral Orbit Tribometer (SOT)," International Spring Fuels & Lubricants Meeting & Exposition, Paris (France), June 19–22, 2000.
12. Marchetti M., Jones W.R., Jr., Street K.W., Pepper S.V., Jansen M.J., "Preliminary Evaluation of Greases for Space Mechanisms Using a Vacuum Spiral Orbit Tribometer," NLGI 68<sup>th</sup> Conference, West Palm Beach (Florida), October 27–31 2001.
13. Marchetti M., Jones W.R., Jr., Street K.W., Wheeler D., Dixon D., Jansen M.J., Kimura H., "Tribological Performance of Some Pennzane<sup>®</sup> Based Greases for Vacuum Applications." *Tribology Letters* (*in press*).
14. Marchetti M., Jones W.R., Jr., "Degradation of PFPE Based Greases under Ultrahigh Vacuum" (*to be published*).
15. Prat P., Ph.D. Thesis, INSA Lyon, France (97 ISAL 018), 14<sup>th</sup> February 1996.
16. Jansen M.J., Jones W.R. Jr., Wheeler D.R., "Evaluation of Non-Ozone-Depleting-Chemical Cleaning Methods for Space Mechanisms Using a Vacuum Spiral Orbit Rolling Contact Tribometer," *Lubrication Engineering*, vol. 57, n° 10, October 2001, pp. 22–26.
17. Jones W.R. Jr., Pepper S.V., Wheeler D.R., Jansen M.J., Nguyen Q., Schröer A., "The Effect of Stress and TiC Coated Balls on Lifetime of a Perfluoropolyalkylether Using a Vacuum Rolling Contact Tribometer". *Tribology Transactions*, volume 43 (2000), 4, pp. 685–688.
18. Shogrin B., Jones W.R. Jr., Wilbur P.J., Herrera-Fierro P., Williamson D.L., "The Effects of Ion Implantation on the Tribology of Perfluoropolyether-Lubricated 440C Stainless Steel Couples," NASA TM-106965, August 1995.
19. Carré D.J., "The Use of Ceramic and Ceramic Hard-Coated Components to Prolong the Performance of Perfluoropolyalkylether Lubricants," Aerospace Corporation Report SSD-TR-90-32, 30 September 1990.
20. Vukasovich M.S., Kelly W.D., "The Effect of MoS<sub>2</sub> on the Performance of Some Model Greases," *Lubrication Engineering*, vol. 28, April 1972, pp. 125–134.

	MAC-greases		
	MAPLUB® SH050	MAPLUB® SH051	Rheolube® 2000
appearance	white	black	light brown
base oil	MAC	MAC	MAC
additive(s)	none	MoS <sub>2</sub>	a phosphate, an amine and a hindered phenol
thickener	PTFE	PTFE	soap of sodium n-octadecylterephthalamate
dropping point (°C)	<i>N/A</i>	<i>N/A</i>	> 260
worked penetration (60 strikes, 25°C)	348	365	276
oil separation (mass %)	4.2 (100 °C, 30 h)	3.8 (100 °C, 30 h)	3.3 (100 °C, 24 h)
temperature range min/max (°C)	-40 / 200	-40 / 200	-45 / 125
NLGI grade	0-1	0	2
	PFPE-greases		
	MAPLUB® PF100	MAPLUB® PF101	Krytox® 240AC
appearance	white	black	white
base oil	linear PFPE	linear PFPE	branched PFPE
additive(s)	none	MoS <sub>2</sub>	none
thickener	PTFE	PTFE	PTFE
dropping point (°C)	<i>N/A</i>	<i>N/A</i>	<i>N/A</i>
worked penetration, 60 strikes (25°C)	269	281	265-295
oil separation (mass %)	2.7 (100 °C, 30 h)	3.3 (100 °C, 30 h)	3.0 (99 °C, 30 h)
temperature range min/max (°C)	-60 / 130	-60 / 130	-35 / 285
NLGI grade	2	2	2

Table 1: Grease compositions and properties




Figure 1: The Spiral Orbit Tribometer






Figure 2: Normalized lifetimes of the test greases (with standard deviation)






(a) grease MAPLUB® SH050




(b) grease MAPLUB® SH051




(c) grease Rheolube® 2000 [13]


Figure 3: Examples of friction coefficient traces for MAC-greases



(a) grease MAPLUB<sup>®</sup> PF100



(b) grease MAPLUB<sup>®</sup> PF101



(c) grease Krytox<sup>®</sup> 240AC

Figure 4: Examples of friction coefficient traces for PFPE-greases





Figure 5: XPS and EDAX spectra of the scrub zone indicating the presence of a fluorocarbon product and the absence of  $\text{MoS}_2$



REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE September 2002		3. REPORT TYPE AND DATES COVERED Technical Memorandum
4. TITLE AND SUBTITLE  Relative Lifetimes of MAPLUB® Greases for Space Applications			5. FUNDING NUMBERS  WU-274-00-00-00	
6. AUTHOR(S)  Mario Marchetti, William R. Jones, Jr., and Jacques Sicre				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)  National Aeronautics and Space Administration John H. Glenn Research Center at Lewis Field Cleveland, Ohio 44135-3191			8. PERFORMING ORGANIZATION REPORT NUMBER  E-13557	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)  National Aeronautics and Space Administration Washington, DC 20546-0001			10. SPONSORING/MONITORING AGENCY REPORT NUMBER  NASA TM-2002-211875	
11. SUPPLEMENTARY NOTES  Mario Marchetti, National Research Council—National Research Associate at Glenn Research Center; William R. Jones, Jr., NASA Glenn Research Center; and Jacques Sicre, Centre National D'Etudes Spatiales, Département Mécanismes, 18 avenue Edouard Belin, BPi 1416, 31055 Toulouse cedex, France. Responsible person, Mario Marchetti, organization code 5960, 216-433-5843.				
12a. DISTRIBUTION/AVAILABILITY STATEMENT  Unclassified - Unlimited Subject Category: 27  Available electronically at <a href="http://gltrs.grc.nasa.gov">http://gltrs.grc.nasa.gov</a> This publication is available from the NASA Center for AeroSpace Information, 301-621-0390.			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words)  A Spiral Orbit Tribometer was employed to evaluate the tribological behavior and relative lifetimes of several commercially available greases under ultrahigh vacuum. These greases are either based on a multiply alkylated cyclopentane oil, or a perfluoropolyalkylether oil, and a thickener made of polytetrafluoroethylene (PTFE) telomer. The multiply alkylated cyclopentane (MAC) greases yielded long lifetimes, while perfluoropolyalkylether (PFPE) greases yielded short lifetimes.				
14. SUBJECT TERMS  Spiral orbiter tribometer; Space mechanisms			15. NUMBER OF PAGES 16	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT  Unclassified	18. SECURITY CLASSIFICATION OF THIS PAGE  Unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT  Unclassified	20. LIMITATION OF ABSTRACT	